



FEB 24 1995

RECEIVED

FEB 08 1995

Corres. and Mail

GROUP 3200

BOX AF

BOX AF EXPEDITED PROCESSING
UNDER 37 CFR 1.116

IN THE US PATENT AND TRADEMARK OFFICE

Janaury 30, 1995

Applicants: Iver E. Anderson, et al.

For : Pb-FREE Sn-Ag-Cu TERNARY EUTECTIC SOLDER

Serial No.: 08/094 854

Group: 3205

Filed : July 20, 1993

Examiner: Knapp

Atty. Docket
No. ISU Case 340

The Commissioner of Patents and Trademarks
Washington, D.C. 20231

RESPONSE UNDER 37 CFR 1.116

Dear Sir:

Please amend the above-identified application as follows:

In the Claims

a) Cancel claim 21 without prejudice.

b) Please amend the following claims:

1. (Twice Amended) A Pb-free electrical conductor solder consisting essentially of about 3.5 to about 7.7 weight % Ag, about 1.0 to about 4.0 weight % Cu and the balance essentially Sn wherein Sn is present in an amount of at least about 89 weight % Sn to promote formation of intermetallic compounds that improve solder wettability on the electrical conductor, said solder being free of Ti, V, and Zr.

6. (Twice Amended) A Pb-free electrical conductor solder including a ternary eutectic composition consisting essentially of about 93.6 weight % Sn-about 4.7 weight % Ag-1.7 weight % Cu having a eutectic melting temperature of about 217°C and variants of said ternary eutectic composition wherein the relative concentrations of Sn, Ag, and Cu deviate from said ternary eutectic composition to provide a controlled [melting] liquid plus solid mushy temperature range with a liquidus temperature not exceeding 15°C above said eutectic melting temperature and at least two intermetallic compounds dispersed in a beta Sn matrix wherein one intermetallic compound includes Cu and Sn and another intermetallic compound